



DUST
REDUCED

Sika[®] Level-425

DUST REDUCED, SELF-LEVELING UNDERLAYMENT

- Innovative dust reduction technology
- Acceptable for castor wheel above 1/8" thickness
- Extremely low shrinkage

Available in
55 lb. bag



BUILDING TRUST



Sika® Level-425

DUST REDUCED, SELF-LEVELING UNDERLAYMENT

WHERE TO USE

- Interior use only
- Levels, flattens and smooths substrates before application of resilient floor
- Suitable on concrete, ceramic and quarry tile, OSB/Plywood, well bonded LVT
- Used in libraries, domestic properties, industrial facilities, cafeterias

FEATURES AND BENEFITS

- Innovative dust reduction technology
- Very low shrinkage
- Extremely high flow and smooth
- Compatible with subfloor heating systems
- Suitable for use in the Sika® Secure System
- Install most floor covering in 16 hours

NOTE: Always refer to current PDS and SDS for detailed performance specifications prior to use.

TYPICAL DATA (Material and curing conditions @ 73°F (23°C) and 50% R.H.)	
Color	Concrete Gray
Application Thickness	1/8" up to 1/2" (3 mm up to 13 mm) Can be extended with aggregate to 1" (25 mm)
Density (ASTM C185)	118 lbs/cu.ft.
Working Time	Approx. 30 minutes
Ready for Foot Traffic	Approx. 3 hours
Flexural Strength (ASTM C348)	1,000 psi (6.9 MPa) at 28 days
Compressive Strength (ASTM C109)	5,600 psi (38.6 MPa) at 28 days
VOC (EPA METHOD 24)	0 g/l

Sika® Classification Table					
Strength					
Flow					
Depth					
Speed					



FOR MORE INFORMATION:

Contact Sika: Phone 800.933.SIKA(7452) Website: www.sikasecure.com

Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
Phone: 201-933-8800
Fax: 201-933-6225



BUILDING TRUST

